

ENVIRONMENTAL CONTROL TECHNOLOGIES
LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
<u>Dining Room</u>												
W	.5	.4	.5	.46								Negative
CE	.8	.6	.4	.60	.7	.7	.6	.66	0			Negative
CM	.1	.3	.3	.23								Negative
BB	10.0	10.0	10.0	10.0								Abate
Baseheater/Metal	1.7	1.4	1.3	1.43	.3	.3	.3	.30	1.10	807-1	248 ppm	NEGATIVE
MD	1.1	1.0	.9	1.0	.9	.8	.8	.83	.17			Negative
EDC	7.9	7.8	7.4	7.7								Abate
DJ	10.0	10.0	10.0	10.0								Abate
IDC	10.0	10.0	10.0	10.0								Abate
WS	10.0	10.0	10.0	10.0								Abate
WA	10.0	9.7	9.6	9.76								Abate
WC	10.0	10.0	9.7	9.90								Abate

Windows are aluminum

ENVIRONMENTAL CONTROL TECHNOLOGIES
LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
<u>Kitchen</u>												
W	.1	.1	.1	.10								Negative
CE	.2	.3	.2	.23								Negative
Radiator	.7	.8	.7	.73	.6	.4	.6	.53	.20			Negative
D/Yellow #1	.1	.2	0	.10								Negative
D/Tan #1	0	.2	.1	.10								Negative
EDC #1	2.9	3.6	3.4	3.30								Abate
IDC #1	.1	.3	.2	.20								Negative
DJ #1	10.0	10.0	10.0	10.0								Abate
D #2	.1	0	.1	.06								Negative
EDC #2	.2	.3	.2	.23								Negative
IDC #2	.2	.2	.2	.20								Negative
DJ #2	10.0	10.0	10.0	10.0								Abate

MD #3 .8 .7 .7 .73 .6 .7 .7 .66 .07 Negative

ENVIRONMENTAL CONTROL TECHNOLOGIES
LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
CM	.4	.4	.4	.40								Negative
BB	.2	.2	.2	.20								Negative
WC	10.0	9.8	9.7	9.83								Abate
WS	4.3	4.5	4.0	4.26								Abate
WA	10.0	9.4	9.7	9.7								Abate
EDC	0	0	0	0								Negative
IDC	0	0	0	0								Negative
DJ	0	0	0	0								Negative
<u>Bdrm #1/Down</u>												
W	.1	0	.1	.06								Negative
CE	0	0	0	0								Negative
BB	1.5	1.1	1.4	1.33	.4	.5	.4	.43	.90	807-2	7027 ppm	ABATE
WC	1.0	.7	.7	.80	.4	.4	.4	.40	.40			Negative

ENVIRONMENTAL CONTROL TECHNOLOGIES

LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
DJ	7.5	7.1	6.9	7.16								Abate
SB/Coat Rack	8.2	8.0	7.6	7.93								Abate
Stairway												
W	0	0	0	0								Negative
CE	.2	.3	.2	.23								Negative
IDC	6.7	6.1	6.0	6.26								Abate
EDC	10.0	10.0	10.0	10.0								Abate
DJ	10.0	10.0	9.4	9.8								Abate
Hand Rail	0	0	0	0								Negative
Stair Stringer	6.6	5.9	6.1	6.2								Abate
BB	8.3	7.6	7.4	7.76								Abate
Stair Header	8.1	7.6	7.4	7.70								Abate
Stair Post	.4	.4	.5	.43								Negative

Stairs covered with carpet

ENVIRONMENTAL CONTROL TECHNOLOGIES
LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
IDC	.2	.1	.1	.13								Negative
DJ	.2	.2	.2	.20								Negative
SB	6.0	5.4	5.4	5.6								Abate
<u>Bedroom #3</u>												
WS	6.1	5.8	5.4	5.76								Abate
WA	10.0	9.6	9.1	9.56								Abate
WC	10.0	10.0	10.0	10.0								Abate
Baseheater/Metal	1.7	1.7	1.8	1.73	.3	.4	.3	.33	1.40			Abate 1.40
<u>Bdrm #3 Closet 2</u>												
EDC	.1	.1	.1	.10								Negative
IDC	.2	.1	.2	.16								Negative
DJ	.1	.3	.1	.16								Negative
W	.3	.2	.1	.20								Negative

CE .3 .2 .2 .23

Negative

ENVIRONMENTAL CONTROL TECHNOLOGIES
LBP XK-3 SAMPLE SHEET

Date/Time: March 11, 1993 Apartment # 807 Hancock Project: Area 8 Site: Erie Metro. H.A.

Sample Number	Reading (mg/cm ²)				S.E.L. (mg/cm ²)				C.L.C. (mg/cm ²)	Conformation Test		Result Neg./Abate
	1	2	3	Avg	1	2	3	Avg		No.	Result	
BB	5.4	5.1	5.0	5.16								Abate
<u>Exterior</u>												
Green Siding	5.1	4.9	5.0	5.0								Abate
Porch Beam	10.0	9.4	9.7	9.70								Abate
Porch Post/Met.	1.0	1.1	1.0	1.03	.7	.7	.9	.76	.27			Negative
Porch Ceiling	0	0	0	0								Negative
Tan Siding	.6	.4	.4	.46								Negative
Soffitt	0	0	0	0								Negative
Facia Board	8.7	8.5	8.1	8.43								Abate
Green HR/Metal	1.2	1.1	1.0	1.1	.9	.7	.7	.76	.34			Negative

Windows covered with aluminum